MIGRATORY CORROSION INHIBITOR (MGI®) PRODUCTS FOR CONCRETE





MCI®-2005 Gel



PRODUCT DESCRIPTION

MCI®-2005 Gel utilizes MCI®-2005 admixture chemistry in a gel format for injection into cracks and cores in concrete. MCI®-2005 Gel is designed to get MCI® molecules closer to embedded reinforcing steel to provide corrosion protection more quickly than surface applied products. It offers the time-proven Migrating Corrosion Inhibitor (MCI®) technology for corrosion protection of reinforcing steel and metals in concrete. MCI®-2005 Gel releases a vapor into the concrete that migrates, seeks out and coats reinforcing steel and metals, stopping further corrosion and extending the service life of the structure.

WHERE TO USE

MCI®-2005 Gel is recommended for:

- Steel-reinforced concrete bridges, exposed to corrosive environments (carbonation, deicing salts and atmospheric attack)
- Parking decks, ramps and garages
- All reinforced marine concrete structures and dams
- Concrete piers, piles, and pillars
- Balconies, decks, retaining walls, and lanais
- Concrete equipment bases
- Structural walls, below grade tunnels and structures
- All reinforced concrete commercial and civil engineered structures

ADVANTAGES

- Offers engineers, owners, contractors, DOTs and government agencies a unique opportunity for corrosion protection that will extend the life of all reinforced concrete structures
- Protects against the harmful effects of corrosion even in the densest concrete
- Required dosage is not affected by chloride concentration
- Economical to install and maintain
- Organic, safe and environmentally friendly
- Concentrated for cost effectiveness on all projects
- Protects both anodic and cathodic areas
- Will migrate to adjacent areas to protect surrounding metals
- Effective against corrosives such as salts, sulfur and nitrogen oxides
- Solves corrosion problems in areas where surface corrosion treatments cannot be used

ESTIMATED HOLES FILLED APPLICATION CHART

	5 gal (19 Liters)	55 gal (208 Liters)	10.3 oz Tubes (0.304 Liters)
3/4"x2" (1.9x5.1 cm)	1307	14379	20
3/4"x3" (1.9x7.6 cm)	871	9586	13
3/4"x4" (1.9x10.2 cm)	654	7190	10
3/4"x5" (1.9x12.7 cm)	523	5752	8
3/4"x6" (1.9x15.2 cm)	436	4793	7
3/4"x7" (1.9x17.8 cm)	373	4108	6
3/4"x8" (1.9x20.3 cm)	327	3595	5
3/4"x9" (1.9x22.9 cm)	290	3195	5
3/4"x10" (1.9x25.4 cm)	261	2876	4



APPLICATION

MCI®-2005 Gel is injected into predrilled ¾" (1.9 cm) diameter holes by a hand-held caulking gun or power inductor plate bulk pump, to the level at which the patch will be placed.

APPLICATION CHART

Conventional bridges and parking ramps using standard concrete mix designs specifications similar to ASTM C 1439 should follow this application chart. The depth of the core drilled should equal the depth of reinforcement to be protected.

2" (5.1 cm), approx. 18" (45.7 cm) apart 3" (7.6 cm), approx. 22" (55.9 cm) apart 4" (10.2 cm), approx. 25" (63.5 cm) apart 5" (12.7 cm), approx. 28" (71.1 cm) apart 6" (15.2 cm), approx. 30" (76.2 cm) apart 7" (17.8 cm), approx. 33" (83.8 cm) apart 8" (20.3 cm), approx. 35" (88.9 cm) apart 9" (22.9 cm), approx. 37" (94.0 cm) apart 10" (25.4 cm), approx. 39" (99.1 cm) apart

Note: MCI® corrosion protection starts within a few weeks of installation. The integrity of the structure should be checked by a qualified structural engineer. Placement patterns should be verified by this engineer. Additional spalling of concrete may take place after installation of MCI® due to prior corrosion activity even though corrosion protection by the MCI® has started to work.

FOR INDUSTRIAL USE ONLY
KEEP OUT OF REACH OF CHILDREN
KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION
CONSULT MATERIAL SAFETY DATA SHEET FOR MORE
INFORMATION

TYPICAL PROPERTIES

Appearance Dark brown gel Flash Point >202°F (100°C)

Shelf Life 12 months in a sealed container

Non-volatile Content 65-75%

Density 10.0-11.0 lb/gal (1.20-1.32 kg/l)

PACKAGING

MCI®-2005 Gel is available in 10.3 oz. (304 mL) caulking tubes, 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes and bulk.

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA Phone (651) 429-1100, Fax (651) 429-1122 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com Internet http://www.CortecVCI.com

printed on recycled paper 100% post consumer
Revised 10/09/06. Cortec Corporation 2002-2006. All rights reserved. Supersedes:6/27/06.
MCI® is a trademark of Cortec Corporation.
© 2002-2006, Cortec Corporation. All Rights Reserved. Copyring of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.