VpCI®-385



PRODUCT DESCRIPTION

VpCI-385 is a water-based acrylic coating specifically designed to provide a non-skid surface on metal substrates while providing VpCI corrosion protection*. VpCI-385 has long-lasting aggregates and film properties formulated for floors, providing excellent wear resistance. VpCI-385 can be brushed or rolled.

FEATURES

- Good adhesion
- Non-skid surface
- Multimetal protection
- Excellent slip resistance
- Excellent wear resistance
- Color match

*It is advised to use a primer such as Cortec® VpCl-373 or VpCl-375 when coating over cleaned steel. This provides better protection, surface coverage, and a barrier cushion between the aggregate and substrate.

APPLICATION

Surface Preparation:

NACE	SSPC	ARS
3	6	Low A-3

NACE - National Association of Corrosion Engineers

SSPC - Steel Structure Painting Council ARS - American Rust Standard Guide

Product Preparation:

VpCI-385 should be thoroughly mixed prior to use as settling occurs over time. Use dispersion blade for best results.

Product Application:

Product can be applied by brush or roll. Normal coverage area is 65-75 ft²/gal (1.6-1.8 m²/l)

Product Cleanup:

Use water to clean up tools and overspray.

TYPICAL PROPERTIES

Appearance Liquid, various colors

Dry to Cure Time 48 hours
Dry to Recoat Time 6-18 hours

Dry to Touch Time 30-120 minutes (depending on

ambient conditions)

Film Type Hard, non-skid

Non-volatile Content 35-45%

 Shelf Life
 12 months @ 75°F (24°C)

 Theoretical Coverage
 65-75 ft²/gal (1.6-1.8 m²/l)

 VOC (regulatory)
 1.6-1.7 lb/gal (192-204 g/l)

 VOC (actural)
 0.6-0.7 lb/gal (72-84 g/l)

Density 8.6-9.3 lb/gal (1.03-1.11 kg/l)

Note: Coating dry time is affected by temperature, air flow, and humidity.

LIMITATIONS

Avoid using VpCI-385 in situations where the coating is immersed in water or other liquids. This could lead to a softening of the film.

STORAGE AND PACKAGING

VpCI-385 is available in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes, and bulk. Do not allow product to freeze.



FOR INDUSTRIAL USE ONLY KEEP OUT OF REACH OF CHILDREN KEEP CONTAINER TIGHTLY CLOSED NOT FOR INTERNAL CONSUMPTION CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within is xi months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Corhec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITHORS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



Distributed by:

4119 White Bear Parkway, St. Paul, MN 55110 USA Phone (651) 429-1100, Fax (651) 429-1122 Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com Internet http://www.cortecvci.com

printed on recycled paper 100% post consumer Revised 2/22/11. Cortec Corporation 1998-2011. All rights reserved. Supersedes: 2/26/07. © 2011, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.